

Robur Flash ECF

Pulp characteristics

Property	Standard	Unit	Drainage resistance °SR			
			15	20	25	30
Beating energy, PFI	ISO 5267-1	Rev.	1900	4800	6900	8600
Density	ISO 534	kg/m ³	650	700	730	740
Bulk	ISO 534	cm ³ /g	1.5	1.4	1.4	1.4
Tensile index	ISO 1924-3	kNm/kg	71	95	102	104
Tear index	ISO 1974	Nm ² /kg	18	13	12	11
Burst index	ISO 2758	MN/kg	5,4	7,3	7,8	8,1
Opacity	ISO 2471	%	62	59	57	56
Light Scattering Coeff	ISO 9416	m ² /kg	22	19	18	17
Air permeability, Gurley	ISO 5636-5	mm/kPa s	66	21	10	5

Property	Standard	Unit	
Brightness	ISO 2469	% ISO	88.0
Ash	ISO 1762	%	0.2
Extractives (acetone)	ISO 14453	%	< 0.05

Testing climate: 50% RH, temp: 23 °C

Additional comments: All values are nominal.



Certificates

Chain of custody/Controlled wood	Available on request
Conformity with food contact materials	Normpack certificate
EU Ecolable	Approved pulp for EU Ecolable
Nordic Ecolabel	Approved pulp for Nordic Ecolabel



Technical Data Sheet

Robur Flash ECF

Document number:
R0244-8
Issue date:
2023-10-16

Packaging information

		Bales (LxWxH)	Units (LxWxH)
Number of bales			8
Gross weight	kg	200	1600
Dry content	%		89
Size (H = avg height)	cm	90x60x40	90x120x160
Number of wires		0	7
Wrapping		Bleached Kraft paper	

General information

Wood species:	Spruce and Pine
Digester type:	Continuous
Oxygen delignification	2-stage
Producing mill	Bleaching:
Drying	Flash dried
Producing mill	Vallvik

